

Electronic properties of metal-induced gap states formed at alkali-halide/metal interfaces

Manabu Kiguchi^{1*}, Genki Yoshikawa², Susumu Ikeda², and Koichiro Saiki^{1,2}

¹*Department of Complexity Science & Engineering, Graduate School of Frontier Sciences, The University of Tokyo, Hongo, Bunkyo-ku, Tokyo 113-0033, Japan*

²*Department of Chemistry, The University of Tokyo, Hongo, Bunkyo-ku, Tokyo 113-0033, Japan*
(February 2, 2008)

The spatial distribution and site- distribution of metal induced gap states (MIGS) are studied by thickness dependent near edge x-ray absorption fine structure (NEXAFS) and comparing the cation and anion edge NEXAFS. The thickness dependent NEXAFS shows that the decay length of MIGS depends on rather an alkali halide than a metal, and it is larger for alkali halides with smaller band gap energy. By comparing the Cl edge and K edge NEXAFS for KCl/Cu(001), MIGS are found to be states localizing at anion sites.

PACS numbers: 73.20.-r, 73.40.Ns

The electronic structure of semiconductor/metal or insulator/metal interfaces has attracted wide attention in relation to intriguing phenomena, such as band gap narrowing, insulator-metal transition, excitonic superconductivity [1–3]. One of the characteristic electronic structures at the interfaces is formation of a metal-induced gap state (MIGS). At the semiconductor (or insulator)/metal interface, a free-electron-like metal wave function penetrates into a semiconductor (or insulator) side, and thus, an interface electronic states (MIGS) is formed in the band gap [4]. The MIGS has been considered to determine the Schottky barrier height at the semiconductor/metal interface [5].

While the decay length of MIGS is an order of a few angstroms for typical semiconductors, it has generally been believed that the decay length of the MIGS into the insulator is negligible. This view is based on quite a plausible tight-binding model calculation [6]. For a typical ionic insulator such as LiCl with the band gap of 9.4 eV, the decay length is estimated to be smaller than 0.1 nm, which suggests that MIGS should be irrelevant at the insulator/metal interface. However, we have obtained an unambiguous evidence that MIGS are formed at atomically well-defined LiCl/metal interfaces by measuring near-edge x-ray absorption fine structure (NEXAFS) [7–9]. With a decreasing LiCl thickness, a well pronounced pre-peak appears at the bulk edge onset in NEXAFS, suggesting formation of an interface state in the band gap. The results of electron spectroscopies (X-ray photoemission spectroscopy and Auger electron spectroscopy), and theoretical calculation indicate that the pre-peak originates not from the simple chemical bond but from the proximity of ionic material to metals. Furthermore, it has been revealed that the decay length of MIGS is as large as 0.3 nm and that the MIGS have a p_z like structure, extending its electron cloud along the surface normal direction (parallel to z -axis).

Although we have revealed the existence of novel elec-

tronic states, MIGS, at the LiCl/metal interface, there still remains points to be discussed. First, the decisive factor to determine the decay length of MIGS is not clear at the alkali halide/metal interface. What is the decisive factor; metal substrates, alkali halides, or their combinations? Second, it is not clear whether MIGS extend uniformly in the surface parallel direction or they are localized at anion or cation site.

In order to determine the decisive factor, we have measured NEXAFS for KCl/metal, and discussed the decay length of MIGS at the alkali halide/metal interface by comparing the previous LiCl/metal results. To determine the site-distribution of MIGS, we have studied K-edge and Cl-edge NEXAFS for KCl/metal. NEXAFS qualitatively provides information on the unoccupied p electronic density of states of the x-ray absorbing atom. By comparing the intensity of the MIGS peak in K-edge and Cl-edge NEXAFS for KCl/metal, the density of states of MIGS at K and Cl sites are evaluated. Therefore, we can discuss whether MIGS extend uniformly in the surface parallel direction or they are localized at anion or cation site. Finally we comment on the possibility of interface superconductivity.

The experiments were performed in a custom-designed ultrahigh-vacuum (UHV) system with a base pressure of 1×10^{-7} Pa. A mechanically and electrochemically polished Cu(001) and Ag(001) crystals were cleaned by repeated cycles of Ar sputtering and annealing at 900 K. KCl was evaporated from a Knudsen cell at the substrate temperature of 300 K. The growth rate was monitored using a quartz crystal oscillator, and it was on the order of 1 ML (0.31 nm)/min. Real-time observation of crystallinity of the KCl films was done by reflection high energy electron diffraction (RHEED). Sharp streaks were observed in RHEED patterns of the grown KCl films, indicating that an epitaxial KCl(001) film grew in a layer-by-layer fashion [7,8].

Cl- K and K- K edge NEXAFS measurements were car-

ried out at the soft X-ray double-crystal monochromator station BL-11B of the Photon Factory in High Energy Accelerator Research Organization [10]. The energy resolution of the Ge(111) monochromator was about 1.5 eV. The fluorescence yield detection method was employed to obtain NEXAFS data by using an UHV-compatible gas-flow proportional counter with P10 gas (10 % CH₄ in Ar) as a detector. The Cl 1s X-ray photoemission spectrum (XPS) was measured using X-ray synchrotron radiation at 2900 eV with a RIGAKU XPS-7000 concentric hemispherical analyzer. In the XPS for KCl/metal systems, the width of the Cl 1s peak does not change with the film thickness, nor does a satellite peak appear, indicating that any chemical bond (Cl-Cu or Cl-Ag bonds) is not formed at the KCl/metal interface.

Figure 1 shows the Cl-*K* edge NEXAFS for the epitaxially grown KCl film on Ag(001) and Cu(001) taking at grazing X-ray incidence (15°) for various thicknesses of the KCl layer. All the spectra are normalized by their edge jumps. In the thin film region, a well pronounced pre-peak, which originates from MIGS, appears just below the bulk edge onset. In the following, we would discuss the spatial distribution of the MIGS at the alkali halide/metal interface by analyzing the intensity of this pre-peak.

First, the spatial distribution of MIGS in the surface normal direction is discussed in terms of the decay length of MIGS. Figure 2 shows the intensity of the pre-peak (not normalized by the edge jump unlike Fig. 1) as a function of the film thickness. Here, we assume that the probing depth of NEXAFS is much greater (typically ≥ 1000 nm) than the atomic scale, and the intensity of MIGS($f(x)$) at the distance x from the interface can be represented as $I_0 \exp(-x/\lambda)$, where I_0 , x , and λ are the intensity of MIGS at the interface and decay length, respectively. The intensity of MIGS($F(X)$; film thickness X) observed by NEXAFS is, thus, represented as $I_0 \lambda (1 - \exp(-X/\lambda))$ by integrating $f(x)$ from 0 to X . By fitting the experimental data with $F(X)$, the decay length is determined to be 0.46 nm for KCl/Cu(001), 0.41 nm for KCl/Ag(001), 0.26 nm for LiCl/Cu(001) and 0.29 nm for LiCl/Ag(001). The result for the fitting is included in Fig. 3.

The intensity of MIGS at the interface is 19 (a.u.) for KCl/Cu(001), 7.1 for KCl/Ag(001), 14 for LiCl/Cu(001), and 8.6 for LiCl/Ag(001). It can be found that the decay length of MIGS depends on the kind of alkali halide not on the metal. This conclusion is consistent with the recent theoretical calculation conducted by Arita *et al.* [11] They have evaluated the decay length of MIGS for various alkali halide metal combinations by the *ab initio* calculation, in which they conclude that the decay length of MIGS is close to half the lattice constant of alkali halides. Since the lattice constant of KCl ($L=0.63$ nm) is larger than that of LiCl ($L=0.51$ nm), the present experimental results are consistent with the theoretical

calculation results.

In contrast with the decay length, the intensity of MIGS at the interface depends on the metal substrate. The intensity of MIGS at alkali halide/Cu(001) interface (I_0) is larger than that at alkali halide/Ag(001) interface. This difference can be explained by the density of states of metal substrates near the Fermi energy. Since the penetration of electrons in the metal causes the MIGS, the intensity of MIGS at the interface relates closely with the density of states at the Fermi energy, E_F . The density of states at E_F for Cu is larger than that for Ag (r_s parameter: 2.7 for Cu, 3.0 for Ag). It is, thus, reasonable that intensity of MIGS at the alkali halide/Cu(001) interface is larger than that at alkali halide/Ag(001) interface.

In the previous section, we have discussed the spatial distribution of MIGS in the surface normal direction. We then discuss the spatial distribution of MIGS in the surface parallel direction. The Cl-*K* and K-*K* edges NEXAFS provide information on the unoccupied Cl-p and K-p electronic densities of states. The topmost surface of alkali halide / fcc metal heterostructures is just the (001) face of alkali halide crystal, consisting of the same number of cations and anions. Therefore, we can discuss the site distribution of MIGS in the surface parallel direction by comparing the intensity of the MIGS peak in both Cl edge and K edge NEXAFS for the KCl / metal system. Figure 3 shows Cl-*K* and K-*K* edges NEXAFS for the 1 ML thick KCl film on Cu(001). The pre-peak originating from the MIGS is clearly observed at the Cl edge, while the pre-peak is not observed at the K-edge, indicating that the MIGS are formed only at the anion site. On the other hand, the polarization dependent NEXAFS results show that the MIGS are the states extending their electron cloud along the surface normal direction [9]. Considering these NEXAFS results and our previous calculation results (Fig. 3 in Ref [9]), we can present a systematic view of the spatial distribution of MIGS for the alkali halide/metal interface as seen in Fig. 4.

The localization of MIGS at the anion site can be discussed by considering the calculation results done by Arita *et al.* [11]. Generally, the MIGS can be divided into two groups: one having a conduction band character and the other having a valence band character at the insulator side of the interface. Noguera *et al.* introduced the energy E_{ZCP} which categorizes the character of MIGS [6]. According to their theory, an electronic state has a conduction band character, when its electronic energy is larger than E_{ZCP} , and vice versa. On the other hand, charge transfer between the insulator and the metal is determined by the energy position of E_{ZCP} relative to the Fermi energy (E_F). Charge is transferred from the insulator to the metal, if $E_{ZCP} > E_F$. Arita *et al.* evaluate the charge transfer for various alkali halide/metal combinations by *ab initio* calculations, and found that the charge transfer from the insulator to the metal com-

monly occurs for the alkali halide/metal systems [11]. This indicates that E_{ZCP} is higher than E_F for the alkali halide/metal systems, and thus, the electronic state near E_F has a valence band character. Since the MIGS are electronic states formed near E_F , the MIGS have a valence band character and they are localized at anion site.

Finally, let us point out that the electronic structure specific to alkali halide/metal interfaces can have implications for superconductivity. In the previous study, we propose a possibility of the MIGS working favorably for the exciton-mediated superconductivity [9,11]. In the presence of MIGS at the alkali halide/metal interface, an exciton [associated with the wide band gap of the alkali halide] and carriers (from MIGS) coexist within one atomic distance, the situation of which is favorable for strong interaction between the carriers and the exciton. This strong interaction leads to a possible ground for superconductivity by exciton mechanism proposed by Ginzburg *et al.* [3].

The localization of MIGS at anion sites provides another possibility of superconductivity proposed by Kuroki and Aoki [12]. They propose that repulsively interacting systems consisting of a carrier band and an insulating band can become superconducting, where the system can be effectively mapped to an attractive Hubbard model. In their model, the metallic band is assumed to interact only with the anion sites (or to interact only with the cation sites). Figure 4 shows the Kuroki model, where the carrier band (α) interacts repulsively (V) with the insulating band (β_2). At the alkali halide/metal interface, MIGS have their amplitudes only on anion sites, so that the MIGS should interact primarily with anion sites, which just corresponds to the situation considered in Kuroki model. β_1 , β_2 and α bands in the Kuroki model correspond to the anion, cation and MIGS bands in alkali halide/metal systems, as shown in Fig. 4. So we may envisage that the alkali halide/metal interface may provide a possible ground for superconductivity, although quantitative prediction for T_c could not be done at present stage.

This work was supported by a Grant-in-Aid for Scientific Research and Special Coordination Fund from the Ministry of Education of Japan. (Creative Scientific Research Project, No.14GS0207). The present work was performed under the approval of Photon Factory Program Advisory Committee (PF-PAC No.2001G336).

- Molecules and Atoms, Part A, ed. by J.A. Devreese *et al.* (Plenum Press, 1974)
- [2] R. Arita, Y. Tanida, K. Kuroki and H. Aoki, Phys. Rev. B **64**, 245112 (2001).
 - [3] "High-Temperature Superconductivity" edited by VL Ginzburg, DA Kirzhnits (Consultants Bureau, 1982).
 - [4] S.G. Louie and M.L. Cohen, Phys. Rev. B **13**, 2461 (1976)
 - [5] J. Tersoff, Phys. Rev. Lett. **52**, 465 (1984).
 - [6] C. Noguera and G. Bordier, J. Phys. III (France) **4**, 1851 (1994).
 - [7] M. Kiguchi, K. Saiki, T. Sasaki, Y. Iwasawa, and A. Koma, Phys. Rev. B **63**, 205418 (2001).
 - [8] M. Kiguchi, S. Entani, K. Saiki, H. Inoue, and A. Koma, Phys. Rev. B **66**, 155424 (2002).
 - [9] M. Kiguchi, R. Arita, G. Yoshikawa, Y. Tanida, M. Katayama, K. Saiki, A. Koma and H. Aoki, Phys. Rev. Lett. **90** (2003) 196803.
 - [10] T. Ohta, P. M. Stefan, M. Nomura and H. Sekiyama, Nucl. Instrum. Methods Phys. Res. A **246**, 373 (1986).
 - [11] R. Arita, Y. Tanida, K. Kuroki, and H. Aoki, Phys. Rev. B **69** (2004) 115424.
 - [12] K. Kuroki and H. Aoki, Phys. Rev. Lett. **69** (1992) 3820.





FIG. 1. The Cl-K edge NEXAFS spectra of KCl films grown on Cu(001) and Ag(001) for various thicknesses of the KCl layer taken at the X-ray incidence angle of 15° . All the spectra are normalized by their edge-jump.



* Present address: Department of Chemistry, Hokkaido University, Sapporo 060-0810, Japan.

[1] P.W. Anderson in Elementary Excitation in Solids,

FIG. 2. The intensity of the pre-peak (not normalized by the edge-jump unlike in Fig. 1) versus the film thickness, where the curves indicate the results of least-square fit to $F(X)$. The intensity of the pre-peak for the alkali halide film was obtained by subtracting the bulk component from the spectra.




FIG. 3. The Cl- K and K- K edge NEXAFS spectra of 1 ML thick KCl films grown on Cu(001) taken at the X-ray incidence angle of 15° (line), together with the spectra of bulk KCl (dot line).




FIG. 4. Systematic view of MIGS at the alkali halide/metal interface. The position of cation (box) and anion (circle) is shown in the figure. (Right) Kuroki model and a multi band model of alkali halide/metal interfaces. In the Kuroki model, carrier band (α) interacts repulsively with insulating band (β_2). In the alkali halide/metal system, MIGS band interacts with anion band.